SHERWIN-WILLIAMS.

Technical Data Sheet

DC810

Speedo clear

Product description

Acid catalyst 2 component high gloss multicoat lacquer with very high body. Can be used as a sealer to fill up pores in porous wood species.

Product data

Solid content: [weight %] theoretical 61 ±1

Specific gravity: 990 ±30 [kg/m³]

Viscosity: [s] DIN 4 test performed at 23 °C

Frost sensitive: Nο

At 0-30 °C Storing: 12 months

Storing at higher temperature reduces shelf life, do not expose to direct sunlight

To achive the best result and consistency follow the application and surface temperatures given in 18-30 °C

Process Temperature: Schedule of Apllication for each specific technology and production line.

Mixing/Application

Recommended application **Application** Amount **Application** method Hardener hardener Dilutant viscosity amount Notes [s] DIN 4 $[g/m^2]$ [Parts by vol] Air mix spraying DV309 10 DT890 17-20 80-120 Hardener added to 100 vol parts of paint

Stir well before use!

NT019 Cleaning:

DT890

Drying

Method **Drying condition Drying time** Notes

Air Drying 20 °C 12-16h depends on amount 70°C 30-40 min Forced drying depends on amount

All kind of drying requires good ventilation and circulation

Do not stack before surface temperature below 30 °C

Exterior products: should not be exposed to water, water condensation or temperatures below 0 °C with in 48 h after application

Curing

UV-dose Min UV dose Rec min Peak. Min UV dose Rec min Peak. [mJ/cm2] [mW/cm²] [mJ/cm2] [mW/cm²] Ga Hg lamps (280-320 nm) Hg Ga lamps (390-450 nm)

Full cure N/A N/A Semi cure

Note - Required Peak/Energy is depending on several factors, such as substrate, amount of application, number of layers and type of UV oven / reflectors. Recommended Peak/Energy values will be stated in the finishing instruction/process control submitted by technician.

General information

According to Swedish legislation we provide information regarding dangerous materials. The Safety Data Sheet contains facts about the components, primarily solvents and acids which present the dangerous characteristics. The Safety Data Sheet will be sent on request. All values and recommendations above are to be considered as guidance only. Many factors beyond our control may have an influence on the coating result. Should a problem arise, please contact us and we will advise accordingly. We reserve the right to alter the above specifications.

Date issued: 2017-05-16 (Valid 1 year from issue date) Latest update: 170424