

Technical Data Sheet

DF1346-5200

Vindu Prime

Product description

Two pack acid catalyst primer for exterior doors and door frames. Meets high demands such as high build and appearance. Outdoor durability will be improved by usage of vacuum preservative impregnated wood.

Product data

Gloss: N/A Gardner 60°

Solid content: 75 ±1 [weight %] theoretical

Specific gravity: 1300 ± 30 [kg/m³]

Viscosity: 80-90 [KU] Stormer test performed at 23 °C

Frost sensitive: No

Storing: 12 months At 0-30 °C

Storing at higher temperature reduces shelf life, do not expose to direct sunlight

Process Temperature: 18-30 °C To achive the best result and consistency follow the application and surface temperatures given

in Schedule of Apllication for each specific technology and production line.

Mixing/Application						
Recommended application		Amount		Application	Application	
method	Hardener	hardener	Dilutant	viscosity	amount	Notes
		[Parts by vol]		[s] DIN 4	[g/m²]	
Air mix spraying	DV311	15	DT890	30-35	125-200	Hardener added to 100 vol parts of paint
High speed bell/disc	DV311	15	DT890	30-35	125-200	Hardener added to 100 vol parts of paint

Stir well before use!

Cleaning: DT890

NT019

Drying

Method Drying condition Drying time Notes

Air Drying $20\,^{\circ}\text{C}$ 4-6 h Depends on amount Forced drying $40\,^{\circ}\text{C}$ 1-2 h Depends on amount

All kind of drying requires good ventilation and circulation

Do not stack before surface temperature below 30 °C

Exterior products: should not be exposed to water, water condensation or temperatures below 0 °C with in 48 h after application

Curing

 UV-dose
 Min UV dose
 Rec min Peak.
 Min UV dose
 Rec min Peak.

 [mJ/cm2]
 [mW/cm²]
 [mJ/cm2]
 [mW/cm²]

 Hg lamps (280-320 nm)
 Hg
 Ga lamps (390-450 nm)
 Ga

Full cure N/A Semi cure N/A

Note - Required Peak/Energy is depending on several factors, such as substrate, amount of application, number of layers and type of UV oven / reflectors. Recommended application amounts and Peak/Energy values will be stated in the finishing instruction/process control submitted by technician.

General information

According to Swedish legislation we provide information regarding dangerous materials. The Safety Data Sheet contains facts about the components, primarily solvents and acids which present the dangerous characteristics. The Safety Data Sheet will be sent on request. All values and recommendations above are to be considered as guidance only. Many factors beyond our control may have an influence on the coating result. Should a problem arise, please contact us and we will advise accordingly. We reserve the right to alter the above specifications.

Date issued: **2018-12-14** Latest update: 180925