

## **Technical Data Sheet**

## DH1390-55072

Care Top 25

## **Product description**

Very fast drying topcoat for fast line production. Very good stacking properties. Availible in differnt colors upon request.

**Product data** 

Gloss: 16-20

.0 Gardner 60°

12 months

Solid content: 50 ±1

[weight %] theoretical

Specific gravity: 1050 ±30
Viscosity: 120-130

test performed at 23 °C

Frost sensitive: No

Storing:

At 0-30 °C

[kg/m³]

[s] DIN 4

Storing at higher temperature reduces shelf life, do not expose to direct sunlight

Process Temperature: 18-30 °C

To achive the best result and consistency follow the application and surface temperatures given in

Schedule of Apllication for each specific technology and production line.

.00 vol parts of paint	
.00 vol parts of paint	
.00 vol parts of paint	
L	

Stir well before use!

Cleaning: NT019

DT890

Drying

Method Drying condition Drying time Notes

Forced drying 50  $^{\circ}$ C 30-40 min depends on amount Air Drying 20  $^{\circ}$ C 12-16 h depends on amount

All kind of drying requires good ventilation and circulation Do not stack before surface temperature below 30 °C

Curing

 UV-dose
 Min UV dose
 Rec min Peak.
 Min UV dose
 Rec min Peak.

 [mJ/cm2]
 [mW/cm²]
 [mJ/cm2]
 [mW/cm²]

 Hg lamps (280-320 nm)
 Hg
 Ga lamps (390-450 nm)
 Ga

Full cure N/A Semi cure N/A

Note - Required Peak/Energy is depending on several factors, such as substrate, amount of application, number of layers and type of UV oven / reflectors. Recommended application amounts and Peak/Energy values will be stated in the finishing instruction/process control submitted by technician.

## **General information**

According to Swedish legislation we provide information regarding dangerous materials. The Safety Data Sheet contains facts about the components, primarily solvents and acids which present the dangerous characteristics. The Safety Data Sheet will be sent on request. All values and recommendations above are to be considered as guidance only. Many factors beyond our control may have an influence on the coating result. Should a problem arise, please contact us and we will advise accordingly. We reserve the right to alter the above specifications.

Date issued: **2019-03-01** Latest update: 180926