

Technical Data Sheet

ED1440-9151

Laqvin Fast Dry Prime Bas A

Product description

Waterborne primer for exterior cladding/facade surfaces. Provides a flexible finishing with good outdoor durability. Characteristic for this primer is the very fast drying. This primer should be over coated with a topcoat, preferable EG1540 or WH1560. Possible to over coat directly after drying.

Product data

Gloss:	N/A	Gardner 60°
Solid content:	49 ±1	[weight %] theoretical
Specific gravity:	1240 ±30	[kg/m ³]
pH:	8,5-9	
Viscosity:	60-66	[KU] Stormer
Frost sensitive:	Yes	
Storing:	6 months	At 5-30 °C Storing at higher temperature reduces shelf life, do not expose to direct sunlight
Process Temperature:	18-30 °C	To achieve the best result and consistency follow the application and surface temperatures given in Schedule of Application for each specific technology and production line.

Mixing/Application

Recommended application method	Hardener	Amount hardener [Parts by vol]	Dilutant	Application viscosity	Application amount [g/m ²]	Notes
Air mix spraying			Water	0 - 5 %	150-225	
Air less spraying			Water	0 - 5 %	150-225	
Brush machine			Water	0 - 5 %	150-225	
Vacuumat			Water	0 - 5 %	150-225	

Stir well before use!

Cleaning: Water
XX699

Drying

Method	Drying condition	Drying time	Notes
Air Drying	20-25 °C	6-8 h*	
Forced drying	30-40 °C	6 min*	Drying conditions might need to be optimized
Forced drying IRM	40-50 °C	6 min*	Drying conditions might need to be optimized

* Under optimum conditions total drying time, SW can help you to optimize your drying conditons

All kind of drying requires good ventilation and circulation

Do not stack before surface temperature below 30 °C

Exterior products: should not be exposed to water, water condensation or temperatures below 0 °C with in 48 h after application

Curing

UV-dose	Min UV dose [mJ/cm ²] Hg lamps (280-320 nm)	Rec min Peak. [mW/cm ²] Hg	Min UV dose [mJ/cm ²] Ga lamps (390-450 nm)	Rec min Peak. [mW/cm ²] Ga
Full cure	N/A			
Semi cure	N/A			

Note - Required Peak/Energy is depending on several factors, such as substrate, amount of application, number of layers and type of UV oven / reflectors. Recommended Peak/Energy values will be stated in the finishing instruction/process control submitted by technician.

General information

According to Swedish legislation we provide information regarding dangerous materials. The Safety Data Sheet contains facts about the components, primarily solvents and acids which present the dangerous characteristics. The Safety Data Sheet will be sent on request. All values and recommendations above are to be considered as guidance only. Many factors beyond our control may have an influence on the coating result. Should a problem arise, please contact us and we will advise accordingly. We reserve the right to alter the above specifications.

Date issued: **2017-05-16** (Valid 1 year from issue date)

Latest update: 160809