SHERWIN-WILLIAMS.

Technical Data Sheet

EK1006

Laqva Fill

Product description

Waterborne filler for exterior use. Primarily intended for pine door frames. Can be overcoated by both PU and Waterborne systems. Product application is by extruder to fill small cracks and finger joints openings.

Product data

Gloss: N/A Gardner 60°

Solid content: 73 ±1 [weight %] theoretical

Specific gravity: 1550 ±30 [kg/m³]

Viscosity: 1440000-1760000 [mPas] Viscosimeter test performed at 23 °C

pH: 6-8,5

Frost sensitive: Yes

Storing: 6 months At 5-30 °C

Storing at higher temperature reduces shelf life, do not expose to direct sunlight

To achieve the best result and consistency follow the application and surface temperatures

given in Schedule of Application for each specific technology and production line.

Process Temperature: 18-30 °C

Mixing/Application

Recommended application Amount Application Application method Hardener hardener Diluant viscosity amount Notes

[Parts by vol] [g/m²]

Extruder Water Delivered N/A

Stir well before use!

Cleaning: Water

XX699

Drying

Method Drying condition Drying time Notes

Air Drying Overnight Depends on amount

All kind of drying requires good ventilation and circulation

Do not stack before surface temperature below 30 °C

Exterior products: should not be exposed to water, water condensation or temperatures below 0 °C with in 48 h after application

Curing

 UV-dose
 Min UV dose
 Rec min Peak.
 Min UV dose
 Rec min Peak.

 [mJ/cm2]
 [mW/cm²]
 [mJ/cm2]
 [mW/cm²]

 Hg lamps (280-320 nm)
 Hg
 Ga lamps (390-450 nm)
 Ga

 Full cure
 N/A
 N/A

 Semi cure
 N/A
 N/A

Note - Required Peak/Energy is depending on several factors, such as substrate, amount of application, number of layers and type of UV oven / reflectors. Recommended Peak/Energy values will be stated in the finishing instruction/process control submitted by technician.

General information

According to Swedish legislation we provide information regarding dangerous materials. The Safety Data Sheet contains facts about the components, primarily solvents and acids which present the dangerous characteristics. The Safety Data Sheet will be sent on request. All values and recommendations above are to be considered as guidance only. Many factors beyond our control may have an influence on the coating result. Should a problem arise, please contact us and we will advise accordingly. We reserve the right to alter the above specifications.

Date issued: 2017-05-16 (Valid 1 year from issue date) Latest update: 161219