

# Technical Data Sheet

TF1808-9101

Reafen Proof

## Product description

Two pack solvent borne Polyurethane primer for exterior doors and windows with excellent knot yellowing resistance and meets high demands such as high build, appearance. Outdoor durability will be improved by usage of vacuum preservative impregnated wood. Topcoat must be Laqvin Top EG1507-XXXXX.

## Product data

<b>Gloss:</b>	N/A	Gardner 60°	
<b>Solid content:</b>	72 ±1	[weight %] theoretical	
<b>Specific gravity:</b>	1440 ±30	[kg/m³]	
<b>Viscosity:</b>	100-110	[KU] Stormer	test performed at 23 °C
<b>Frost sensitive:</b>	No		
<b>Storing:</b>	12 months	At 0-30 °C	Storing at higher temperature reduces shelf life, do not expose to direct sunlight
<b>Process Temperature:</b>	18-30 °C		To achieve the best result and consistency follow the application and surface temperatures given in Schedule of Application for each specific technology and production line.

## Mixing/Application

Recommended application method	Hardener	Amount hardener [Parts by vol]	Dilutant	Application viscosity	Application amount [g/m²]	Notes
Air mix spraying	TV805	30	NT019	20-35 s DIN 4	125-200	Hardener added to 100 vol parts of paint
Air less spraying	TV805	30	NT019	20-35 s DIN 4	125-200	Hardener added to 100 vol parts of paint
Conventional spraying	TV805	30	NT019	20-35 s DIN 4	125-200	Hardener added to 100 vol parts of paint

**Stir well before use!**

**Cleaning:** NT019  
DT890

## Drying

Method	Drying condition	Drying time	Notes
Air Drying	20 °C	> 6 h	To handling
Forced drying	30-40 °C	2-4 h	To handling

All kind of drying requires good ventilation and circulation

Do not stack before surface temperature below 30 °C

Exterior products: should not be exposed to water, water condensation or temperatures below 0 °C with in 48 h after application

## Curing

UV-dose	Min UV dose [mJ/cm²]	Rec min Peak. [mW/cm²]	Min UV dose [mJ/cm²]	Rec min Peak. [mW/cm²]
	Hg lamps (280-320 nm)	Hg	Ga lamps (390-450 nm)	Ga
<b>Full cure</b>	N/A		N/A	
<b>Semi cure</b>	N/A		N/A	

Note - Required Peak/Energy is depending on several factors, such as substrate, amount of application, number of layers and type of UV oven / reflectors. Recommended Peak/Energy values will be stated in the finishing instruction/process control submitted by technician.

## General information

According to Swedish legislation we provide information regarding dangerous materials. The Safety Data Sheet contains facts about the components, primarily solvents and acids which present the dangerous characteristics. The Safety Data Sheet will be sent on request. All values and recommendations above are to be considered as guidance only. Many factors beyond our control may have an influence on the coating result. Should a problem arise, please contact us and we will advise accordingly. We reserve the right to alter the above specifications.

Date issued: 2017-05-16 (Valid 1 year from issue date)

Latest update: 2016-06-29